


## GEOMEMBRANE.PVC -TECHNICAL DATA SHEET



Test Property	Test Method	Value	Unit	Conditions
Thickness	ASTMD751	2	mm	23° c
Density	ASTMD792	1.407	g/cm3	23° c & 45%H.
Volatile Loss	ASTMD1203	0.09	%	24h at 70°c
Behavior in Water after 1 Day	ASTMD1239	0.15%	%	23° c
Tear Strength	ASTMD1004	120.6	MPa	23° c & 45%H.
Tensile Properties Strength at Break		MD: 14.18 CD: 14.65	MPa	23° c
Elongation	ASTMD638	262	%	23° c
سختی سنجی	ASTMD2240	89	Shore A	24h 23° c

\* در 20° c - لایه شدن اتفاق نمی افتد.

ADD: f4, No.1, right side Areya Alley, Sarv Intersection forward to ketab Square, Saadat Abad, Tehran, Iran.

TEL/FAX: (+9821)22073871

www.psy.co.ir

TEL: (+9821)22084036, 26760723

info@psy.co.ir